



Firma/company: TANNING TECH '99
Artikel/item: Sheep garment nappa
Zustand/condition: Wet-blue
Farbe/colour: Black
Arbeitsgang/process: Direct-process
Gezeichnet/marked: No. 11

Datum/date: Oct. 1999
Rohware/raw material: indonesian sheepskin
kg:
mm: 0,8
% auf/on: shaved weight

Arbeitsgang process	H ₂ O %	°C	%	Produkt product	Zeit time	Flotte float	Bemerkung remark
wash	200	35	0,20 0,10	NEOPALIN T 106 formic acid	20	drain	pH= 3,6 - 3,8
retanning	150	35	1,00 1,00 1,00 1,50 1,50	LICROL SB 104 EBOTAN DA 50 EBOTAN RAN CHROMOSAL B EBOTAN KL	30 40		
neutralization			2,00 2,00	sodium formate sodium bicarbonate	20 60	drain	pH= 5,6 - 5,8 BCG blue
wash	200	35			10	drain	
dyeing	50	35	0,50 1,00 3,00	ammonia EBROLIN 98 EBOCOR Black 141	20 40		pH= 6,5 - 7,0 check penetration
fatliquoring	100	60	8,00 6,00 2,00 2,50	LICROL ML LICROL 0598 LICROL NW formic acid	10 45 20	drain	pH= 3,6 - 3,8
top-dyeing	200	50	1,00 1,00 1,00	EBOCOR Black 151 liq. formic acid EBROFIX H	10 20 20		
fixing			0,50	EBOCOR Black 151 liq.	20	drain	
wash	200	25			10	drain	

horse up over night, set out, hang dry, condition, staking, dry shave, milling 3 h,
toggle + finish