



**Firma/company:** TANNING TECH '99 **Datum/date:** Oct. 1999  
**Artikel/item:** Gloving leather "cabretta" **Rohware/raw material:** indonesian sheepskin  
**Zustand/condition:** Formaldehyde tanned **kg:**  
**Farbe/colour:** Beige **mm:** 0,45 - 0,55  
**Arbeitsgang/process:** Retanning + fatliquoring **% auf/on:** shaved weight  
**Gezeichnet/marked:** **No. 14**

Arbeitsgang process	H <sub>2</sub> O %	°C	%	Produkt product	Zeit time	Flotte float	Bemerkung remark
wash	200	35	0,20	<b>NEOPALIN T 106</b>	30	drain	
wash	200	35			10	drain	
retanning	100	35	2,00	<b>LICROL SB 104</b>			
			2,00	<b>EBOTAN DA 50</b>	20		
	+		2,00	NOALTAN AL			
			2,00	<b>EBOTAN KL</b>	30		
	+		1,00	sodium acetate	15		
	+		1,50	sodium bicarbonate	45	drain	pH= 5,5 - 5,7
wash	200	50			10	drain	
dyeing	100	50	0,50	ammonia			
			2,00	SELLASOL TN	20		
	+		1,00	<b>EBOCOR Beige 124</b>	30		
fatliquoring	+		11,0	<b>EBENIN 6</b>			
	+		6,00	<b>LICROL G 662</b>	45		
	+		1,50	formic acid	30	drain	pH= 3,6
top-fatliquoring	150	50	2,00	<b>LICROL K 7</b>	20	drain	
wash	200	25			10	drain	

horse up over night, hang dry, staking, milling,  
polish + toggling