



**Firma/company:** TANNING TECH '99 **Datum/date:** Oct.1999  
**Artikel/item:** Gloving leather "cabretta" **Rohware/raw material:** indonesian goatskin  
**Zustand/condition:** Wet-blue **kg:**  
**Farbe/colour:** Black **mm:** 0,45 - 0,55  
**Arbeitsgang/process:** Retanning + fatliquoring **% auf/on:** shaved weight  
**Gezeichnet/marked:** **No. 16**

Arbeitsgang process	H <sub>2</sub> O %	°C	%	Produkt product	Zeit time	Flotte float	Bemerkung remark
wash	200	35	0,10	<b>NEOPALIN T 106</b>			
			0,10	formic acid	20	drain	pH= 3,6 - 3,8
retanning	150	35	2,00	<b>LICROL SB 104</b>			
			3,00	<b>EBOTAN DA 50</b>	20		
			1,50	<b>EBOTAN KL</b>			
			1,50	CHROMOSAL B	40		
			2,00	sodium formate	15		
			3,00	sodium bicarbonate	45	drain	pH= 6,3 - 6,5
wash	200	50			10	drain	
dyeing	100	50	0,50	ammonia			
			1,00	<b>EBROLIN 98</b>	20		
			3,00	<b>EBOCOR Black 141</b>	40		
fatliquoring			12,0	<b>EBENIN 6</b>			
			7,00	<b>LICROL G 662</b>	45		
			2,50	formic acid	20	drain	pH= 3,6 - 3,8
top-dyeing	200	50	2,00	<b>EBOCOR Black 151 liq.</b>	10		
			1,00	formic acid	20		
			1,00	<b>EBROFIX H</b>	20		
wash	200	25			10	drain	

horse up over night, hang dry, staking, dry shaving, milling,  
polishing + toggling