

Date: 18.10.2006

Ref Nr.: 022B

Firma/company: Web Page

Artikel/item: Goat suede shoe

Rohware/raw material: Goat WB

Zustand/condition: Crust

kg:

Farbe/colour:

mm:

0.9-1.0

Arbeitsgang/process: Dyeing

% auf/on:

dry weight

Requirements:

Technician:

CN

Arbeitsgang process	H <sub>2</sub> O %	°C	%	Produkt product	Zeit time	Kontrolle control	Preis/kg price/kg	Kosten cost	Bemerkung remark
Wetting back	800	40	0.5	Neopalin T 106	60'				
			0.5	Ammonia					
Dyeing	250	40	1	Ammonia	20'				
			1	Ebrolin 98					
			6	Dye					
Fatliquoring	250	60	2	Licrol SG	45'				pH 3.8
			2	Licrol 0598					
			2	Formic acid					
			2	Formic acid					
			3	Chrome					
Topdyeing	800	60	4	Dye	40'				
			2	Formic acid					
			2	Ebrofix D					
Wash	800	25		Drain	15'				
			horse, set out, hang, condition, stake, mill, brush, toggle						