



Firma/company: TANNING TECH '99
Artikel/item: Aniline shoe upper
Zustand/condition: Wet- blue
Farbe/colour: Black
Arbeitsgang/process: Retanning, dyeing + fatliquoring
Gezeichnet/marked: **No. 17**

Datum/date: Oct.1999
Rohware/raw material: Java cowhide
kg:
mm: 1,2 - 1,4
% auf/on: shaved weight

Arbeitsgang process	H ₂ O %	°C	%	Produkt product	Zeit time	Flotte float	Bemerkung remark
wash	250	35	0,20	NEOPALIN AP			
			0,10	formic acid	20	drain	pH= 3,4
retanning	150	35	3,00	EBOTAN DA 50	30		
+			3,00	CHROMOSAL B	45		
+			2,00	EBOTAN NFL	20		
+			1,00	sodium bicarbonate			pH= 5,0
+			1,00	LICROL SB 124	45	drain	BCG blue
wash	200	40			10	drain	
dyeing	50	40	1,00	ammonia			
			1,00	EBROLIN 98	15		
+			3,00	EBOCOR Black 141	40		check penetration
fatliquoring	100	60	1,00	LICROL SB 124			
			8,00	LICROL 0598			
			1,00	LICROL L	60		
+			3,00	EBOTAN RAN			
			3,00	MIMOSA			
			3,00	EBOTAN HG	40		
fixing			2,00	formic acid	20	drain	pH= 3,8
top-dyeing	200	50	0,50	EBOCOR Black 151 liq.	10		
+			1,00	formic acid	20		
fixing			0,50	EBROFIX D	20	drain	
wash	200	25			10	drain	

horse up over night, set out, vacuum dry, hang dry, condition,
vibration staking + toggling