



Firma/company: TANNING TECH '99
Artikel/item: Upholstery floater
Zustand/condition: Wet-blue
Farbe/colour: Black
Arbeitsgang/process: Retanning, dyeing + fatliquoring
Gezeichnet/marked: **No. 6**

Datum/date: Oct. 1999
Rohware/raw material: south-g. B 50+
kg:
mm: 1,8-2,0
% auf/on: shaved weight

Arbeitsgang process	H ₂ O %	°C	%	Produkt product	Zeit time	Flotte float	Bemerkung remark
wash	200	35			10	drain	
1.retanning	100	35	2,00	LICROL SB 104	10		
	+		3,00	EBOTAN KL	45		
	+		1,00	sodium formate	20		
neutralization			2,00	EBOTAN RANF	30		
	+		2,00	sodium bicarbonate	120	drain	pH= 6,8 BCG blue
wash	200	35			10	drain	
2.retanning	70	35	4,00	EBOTAN MSC	30		
	+		1,00	EBOTAN G			
			1,00	MIMOSA	30		
dyeing			4,00	EBOCOR Black 141	75		check penetration
fatliquoring	80	60	3,00	LICROL SB 104			
			5,00	LICROL G 662			
			2,00	LICROL LP			
			2,00	LICROL 0598	60		
fixing			2,00	formic acid	2x15	drain	pH= 3,9
top-dyeing	150	50	2,00	EBOCOR Black 151 liq.	20		
	+		0,50	formic acid	20		
	+		1,00	EBOCOR Black 151 liq.	20		
	+		0,50	formic acid	20	drain	pH= 3,5
wash	250	25	1,00	EBROFIX D	20	drain	

horse up over night, set out, toggle to dry, condition, staking + milling 3,0 h